REVISION: 8



DOCUMENT CODE: BEN--PRO1-305

Section I	Product Identification
Manufacturer:	3A Composites USA, Inc. 208 W. 5 th Street, P.O. Box 507 Benton, KY 42025 (270) 527-4200
Emergency Phone Number:	1-800-424-9300 Chemtrec To be used only in the event of chemical emergencies involving a spill, leak, fire, and exposure accidents involving chemicals.
Trade Name:	DIBOND®
Synonym:	Polyethylene / Aluminum Laminated Construction

Section II	Hazard Identification	

DIBOND® is defined as an article under the OSHA Hazard Communications standard. The standard applies to "chemicals" but it does not apply to any substance, which is an "article". The term "article" is defined in the OSHA warning rule, as a manufactured item: 1) which is formed to a specific design during manufacture, 2) which has end use function(s) dependent in whole or in part upon its' shape or design use during end use, and 3) which does not release, or otherwise result in exposure to hazardous chemical under normal conditions of use.

Section III	Chemical Composition	
Ingredients (Common Name)	CAS Number	Percent (%) by weight
Polyethylene	9002-88-4	39-72
Aluminum	7429-90-5	28-61
*Concentration of increasing the demonstration of material		

*Concentration of ingredients depends upon thickness of material.

Section IV	First Aid Measures

This product is not considered to be a health hazard in the form in which they are sold (sheet, panel). However, if these products are abraded, melted, welded, cut or processed in any manner that causes release of fumes or dusts, hazardous levels of fumes or dusts may be generated from this product.

If contact with skin or eyes, wash immediately under water for at least 15 minutes. For inhalation exposure, remove to fresh air. Contact a physician.

Fire Fighting Measures



REVISION: 8

Section VI

DOCUMENT CODE: BEN--PRO1-305

Water, foam, CO ₂ , dry chemical powder
self-contained breathing apparatus should be worn.
May produce water, carbon monoxide, carbon dioxide, and smoke upon combustion

A release should not occur. However, if this product is abraded, melted or cut, dusts may be generated. Should a release of dusts occur, contain by blocking routes to surface water and grassy areas. Clean up by sweeping and depositing into a closed container.

Accidental Release

PPE Requirements: Safety glasses, dust respirator and gloves.



Section VII	Handling and Storage
Storage and handling precautions:	Store in a flat dry area Exercise caution in handling all edges.

Section VIII	Exposure Controls

These products ar rm in which they are sold (sheet, panel). However, if these products are abraded, melted, welded, cut or processed in any manner that causes release of fumes or dusts, hazardous levels of fumes or dusts may be generated from these materials or constituents of these materials. Aluminum fumes or dust are subject to the reporting requirements of section 313 of Title III of the Superfund Amendments and Reauthorization Act of 1986 and 40 CFR Part 372.

Ingredient	OSHA Exposure Limit		ACGIH
	Total	Respirable	TLV
Polyethylene	10mg/m ³	5mg/m ³	N.E.
Aluminum	15mg/m ³	5mg/m ³	N.E.

Effects of overexposure:

Acute:

Physical irritation of the eyes may result from overexposure to high concentrations of dust from certain fabricating operations. Repeated long term inhalation of high concentrations of

respirable dust may cause inflammation of the upper and lower respiratory tract.

	Exposure Controls
re not considered to	be a health hazard in the for

Chronic:

REVISION: 8

DOCUMENT CODE: BEN--PRO1-305

REVISION: 8	DOCUMENT CODE: BENPRO1-
Section IX	Physical and Chemical Properties
Appearance:	Solid Sheet. Sandwich Construction
Odor:	NA
Odor Threshold:	NA
PH:	NA
Melting Point:	Aluminum > 890 °F. Core > 210 °F.
Initial Boiling Point/Boiling Range:	No Data
Flash Point:	Composites - (ASTM D-1929) >784 °F, (418 °C)
Evaporation Rate:	NA
Flammability:	Not Flammable
Upper/lower explosive limit:	NA
Vapor Pressure:	NA
Vapor Density:	NA
Specific Gravity:	Aluminum 2.70-2.73 g/ccm range Core 1.5 -
	1.7 g/ccm range
Solubility:	Insoluble in water
Partition coefficient:	NA
Auto-Ignition:	Composite - (ASTM D-1929) >783 °F (417 °C) Core - N/A
Decomposition Temperature:	No Data
Viscosity:	NA
Section X	Stability and Reactivity
Stability:	Stable
Incompatibility:	None known
Decomposition products:	Reference: "Thermal decomposition", Section V
Section XI	Toxicology Information
No information available	
Section XII	Ecological Information

No information available at this time

Section XIII

Disposal Information

Care must be taken when using or disposing of material debris to prevent environmental contamination. Dispose of the debris in accordance with the Clean Air Act, the Clean Water Act, the Resource Conservation and Recovery Act and all state or local laws / regulations regarding disposal.



REVISION: 8

COMPOSITES

DOCUMENT CODE: BEN--PRO1-305

		DOCUMENT CODE: BENPRO1-3	
Section XIV	Transportation		
UN Number: NA			
UN Proper Shipping Nam	ne: NA		
Transportation Hazard: N	IA		
Packing Group: NA			
Environmental Hazard: N	A		
Transport in bulk: NA			
Special Precautions: NA			

Section XV

Regulatory Information

PROPOSITION 65: (California Only)

Additional Requirements for the State of California: " **WARNING:** This product can expose you to chemicals including ethyl benzene, which is known to the State of California to cause cancer. For more information, go to www.P65Warnings.ca.gov."

REACH: Pursuant to Title II article 7 of the regulation this product is exempt from registration and notification and is therefore compliant with the REACH regulation.

RoHS: DIBOND is compliant with the RoHS standard. All current colors of DIBOND are also compliant with the RoHS standard with the exception of Hunter Red over Caution Yellow and Ultra Marine over Dark Green.

Section XVI

Other Information

Abbreviations:

NA = Not Applicable CAS = Chemical Abstract Service

OSHA = Occupational Safety and Health Administration. PEL = Permissible Exposure Limit STEL = Short Term Exposure Limit. ACGIH = American Conference of Governmental Industrial Hygienist. TLV = Threshold Limit Value.

<u>IMPORTANT:</u> The information and data contained herein are believed to be accurate and have been compiled from sources believed to be accurate. All information contained herein is offered for your consideration, information, investigation, and verification. 3A COMPOSITES MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, CONCERNING THE ACCURACY OR COMPLETENESS OF THE INFORMATION AND DATA HEREIN. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE SPECIFICALLY EXCLUDED. 3A Composites will not be responsible for claims relating to any parties' use of or reliance on information and data contained herein regardless of whether it is claimed that the information are inaccurate, incomplete, or otherwise misleading

REVISION: 8 End of Safety Data Sheet



DOCUMENT CODE: BEN--PRO1-305